



C.T.S. S.R.L.

VIA PIAVE, 20/22 - 36077 **ALTAVILLA VICENTINA (VI)**
TEL. +39 0444 349088 (4 linee r.a.) - FAX +39 0444 349039
www.ctseurope.com - E-mail: cts.italia@ctseurope.com - P.I. e C.F. IT02443840240

Body Accredited by ACCREDIA



FILIALI:

VIA A. F. STELLA, 5 - 20125 **MILANO** - TEL. 02 67493225 (2 linee r.a.) - FAX 02 67493233
VIA L. GORDIGIANI, 54 int. A1-A2 - 50127 **FIRENZE** - TEL. 055 3245014 (2 linee r.a.) - FAX 055 3245078
VIA G. FANTOLI, 26 - 00149 **ROMA** - TEL. 06 55301779 (2 linee r.a.) - FAX 06 5592891
VIA DELLE PUGLIE, 228 int. 4 - 80143 **NAPOLI** - TEL. 081 7592971 - FAX 081 7593118

Scheda Tecnica

BARRE CORRUGATE IN VETRORESINA

CARATTERISTICHE TECNICHE:

Diam.(mm)	Contenuto di fibra di vetro	Contenuto di resina	Resistenza alla tensione (MPa)	Tensione Max (KN)	Modulo di elasticità (GPa)
4	ca. 80%	ca. 20%	890	14	35-41
6	ca. 80%	ca. 20%	825	27	35-41
8	ca. 80%	ca. 20%	760	46	35-41
10	ca. 80%	ca. 20%	720	85	35-41
12	ca. 80%	ca. 20%	690	100	35-41
16	ca. 80%	ca. 20%	655	142	35-41
19	ca. 80%	ca. 20%	620	183	35-41
22	ca. 80%	ca. 20%	586	224	35-41
25	ca. 80%	ca. 20%	550	296	35-41
32	ca. 80%	ca. 20%	480	388	35-41